


ROPES FOR HOISTING EQUIPMENT IN GENERAL

- Bright or galvanized steel
- Wire strength 2160 N/mm²
- Fiber core



F 6x25+FC

Rope Ø mm	outer wire Ø	Mass kg/mt	Minimum breaking load with wire strenght 2160 N/mm ²	
			KN	Kg
7	0,45	0,186	35	3.560
8	0,52	0,243	46	4.650
9	0,58	0,319	58	5.886
10	0,65	0,380	71	7.266
11	0,71	0,460	86	8.792
12	0,78	0,547	103	10.463
13	0,84	0,641	120	12.280
14	0,91	0,745	140	14.241
15	0,97	0,859	160	16.349
16	1,04	0,973	182	18.601
18	1,17	1,230	231	23.542
20	1,29	1,520	285	29.064
22	1,42	1,840	345	35.168
24	1,55	2,190	411	41.852
26	1,68	2,570	482	49.119

ADMINISTRATION AND PRODUCTION : Contrada Cabiano 39,
3065 RIPATRANSONE (AP) TEL. +39 0735 90227 / +39 0735 90278
VAT NUMBER: 02305440444 - EMAIL della.cianci@mpwireropes.com
website: www.metalpress-wireropes.com

METAL PRESS

