


ROPES FOR HOISTING EQUIPMENT IN GENERAL

- Bright or galvanized steel
- Wire strenght 1770, 1960 or 2160 N/mm²
- Metallic core



F 8x25+IWRC

Rope Ø mm	outer wire Ø	Mass kg/mt	Minimum breaking load with wire strenght 1770 N/mm ²		Minimum breaking load with wire strenght 1960 N/mm ²		Minimum breaking load with wire strenght 2160 N/mm ²	
			KN	Kg	KN	Kg	KN	Kg
8	0,42	0,278	41	4.134	45	4.578	49	5.045
9	0,48	0,352	51	5.232	57	5.794	63	6.385
10	0,54	0,435	63	6.459	70	7.153	77	7.883
11	0,57	0,526	77	7.816	85	8.655	94	9.538
12	0,63	0,626	91	9.301	101	10.300	111	11.351
13	0,71	0,732	107	10.916	119	12.088	131	13.322
14	0,73	0,852	124	12.660	138	14.019	152	15.450
15	0,79	0,981	143	14.533	158	16.094	174	17.736
16	0,83	1,110	162	16.536	180	18.311	198	20.179
18	0,94	1,330	205	20.928	227	23.175	251	25.540
20	1,04	1,650	253	25.837	281	28.611	309	31.530
22	1,15	2,060	307	31.263	340	34.619	374	38.152
24	1,25	2,390	365	37.206	404	41.200	445	45.404
26	1,35	2,810	428	43.665	474	48.352	523	53.286
28	1,46	3,250	497	50.641	550	56.077	606	61.799
30	1,56	3,790	570	58.134	632	64.374	696	70.943
32	1,67	4,320	649	66.144	719	73.244	792	80.718
34	1,77	4,870	733	74.670	811	82.685	894	91.122
36	1,88	5,430	821	83.713	909	92.661	1.002	102.158