


ROPES FOR STRUCTURAL APPLICATIONS

- Spiroidal rope with 91 wires
- Galvanized steel class A
- Wire strength 1770 N/mm²



91 wires

Rope Ø mm	outer wire Ø	Mass kg/mt	Minimum breaking load with wire strenght 1770 N/mm ²	
			KN	Kg
30	2,73	4,46	816	83.141
32	2,91	5,07	928	94.596
34	3,09	5,72	1.048	106.790
36	3,27	6,42	1.174	119.723
38	3,45	7,15	1.309	133.396
40	3,64	7,92	1.450	147.807
42	3,82	8,73	1.599	162.957
46	4,18	10,50	1.918	195.474

ADMINISTRATION AND PRODUCTION : Contrada Cabiano 39,
3065 RIPATRANZONE (AP) TEL. +39 0735 90227 / +39 0735 90278
VAT NUMBER: 02305440444 - EMAIL della.cianci@mpwireropes.com
website: www.metalpress-wireropes.com

METAL PRESS

